

## Record Display Form

Page 1 of 1

First HitPrevious DocNext DocGo to Doc#

[REDACTED]

L1: Entry 7 of 8

File: DWPI

DERWENT-ACC-NO: 1973-08518U

DERWENT-WEEK: 197307

COPYRIGHT 2004 DERWENT INFORMATION LTD

TITLE: Heat stable polymethacrylates - prepd in olefin soln and useful in lubricants

PATENT-ASSIGNEE:

ASSIGNEE

CODE

INST FRANCAIS DU PETROLE

INSF

PRIORITY-DATA: 1971FR-0011440 (March 31, 1971)

[REDACTED]

PATENT-FAMILY:

PUB-NO

PUB-DATE

LANGUAGE

PAGES

MAIN-IPC



FR 2131111 A

000

INT-CL (IPC): C08F 1/00; C08F 3/00; C10M 3/00

ABSTRACTED-PUB-NO: FR 2131111A

BASIC-ABSTRACT:

A methacrylate polymer is prepd. by heating  $\geq 1$  methacrylate  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOR}$  (where R is straight or branched chain alkyl), in soln. in  $\geq 1$  3-35C alpha-olefin at 70-120 degrees C, the methacrylate to alpha-olefin molar ratio being 0.1-10, in presence of a free radical initiator. Polymers have improved thermal stability, and are useful in lubricants (esp. for i.c. engines), as VI improvers, thickeners, and pour point depressants.

TI TLE-TERMS: HEAT STABILISED PREPARATION OLEFIN SOLUTION USEFUL LUBRICATE

DERWENT-CLASS: A14 A97 H07

CPI-CODES: A04-F06A; A09-A01A; A12-W02A; H07-G05; H07-G06;

Multipunch Codes: 012 02- 03& 034 05& 051 074 077 081 082 084 145 231 250 264 266  
267 28& 297 31- 316 331 347 352 355 357 41- 44& 541 575 583 589 644 679 688 691 724Previous DocNext DocGo to Doc#